

Palace

CERAMIC & PORCELAIN
STONE COLLECTION



CTS | Pro+

Palace CALACATTA

CTS | Pro⁺



Glossy Ceramic Wall Tile

CTPPACA1224LW




-12x24-

CTPPACA1224LWD



-12x24 curve-

CTPPACABN312LW



-3x12 bullnose-


Matte Porcelain Wall + Floor Tile

CTPPACA1224



-12x24-

CTPPACA24




-24x24-

CTPPACA2448



-24x48 rectified-

CTPPACAMOS22



-2x2 mosaic-

CTPPACABN324



-3x24 bullnose-

CTS Pro+

Palace
DOLOMITE



Glossy Ceramic Wall Tile

CTPPADO1224LW




-12x24-

CTPPADO1224LWD



-12x24 curve-


CTPPADOBN312LW



-3x12 bullnose-

Matte Porcelain Wall + Floor Tile

CTPPADO1224




-12x24-

CTPPADO2448



-24x48 rectified-

CTPPADOMOS22



-2x2 mosaic-

CTPPADOBN324



-3x24 bullnose-




PALACE



CTS | Pro⁺

PRODUCT SPECIFICATIONS - Matte Porcelain Wall + Floor Tile


Suggested Applications




Installation Suggestions



Porcelain Type



Shade Variation



Slip Resistance

DCOF	Values	Applications
0.48	0.42	Recommended Standard DCOF value for wet/dry commercial flooring
	0.65	Recommended Standard DCOF value for ADA ramps

ASTM C-1028
 ANSI A137.1
 DIN 51097/51130

DIN 51130 *R9: Industry Standard/ADA Requirements **R11: Recommended For Exteriors

<input checked="" type="checkbox"/> R9* (3-10°)	<input type="checkbox"/> R10 (10-19°)	<input type="checkbox"/> R11** (19-27°)
<input type="checkbox"/> R12 (27-35°)	<input type="checkbox"/> R13 (>35°)	

DIN 51097

Class	Typical Applications	Critical Angle
<input checked="" type="checkbox"/> A	Barefoot, but mainly dry aisles and walkways, dry changing areas	≥12°
<input type="checkbox"/> B	Shower rooms, pool surrounds, wet changing areas, disinfectant spray areas (plus all Class A areas)	≥18°
<input type="checkbox"/> C	Areas constantly under water, e.g. steps into pools, foot baths, included pool surrounds, jacuzzis (plus all Class A&B areas)	≥24°

Scratch Resistance

MOH'S SCALE
 UNI EN ISO
 10545.6

5

MINERAL

1. Talc (Talc)	6. Microline (Glass, Glazed Tile)
2. Gypsum (Fingernail)	7. Quartz (Unglazed Porcelain)
3. Calcite (Penny)	8. Topaz (Granite)
4. Flourite (Some Marbles)	9. Corundum (Ruby)
5. Apatite (Knife Blade)	10. Diamond (Diamond)

Industry standard ≤175mm²

Wear Resistance

PEI RATING
 UNI EN ISO
 10545.7

- Class 1: Walls only
 - Class 2: Residential floors w/minimal abrasive traffic
 - Class 3: Residential interiors/light commercial traffic
 - Class 4: Medium commercial applications
 - Class 5: All commercial applications/heavy traffic
- *Wear can vary greatly. please consult with a professional.

Stain Resistance

ASTM C1378-04
 UNI EN ISO
 10545.14

5

- 5: Removed after 5 minutes (hot water running)
- 4: Removed by manual cleaning (weak detergent)
- 3: Removed by mechanical cleaning (strong detergent)
- 2: Removed by immersion (24 hrs in suitable solvent)
- 1: Stain not removed

Water Absorption

ASTM C-373
 UNI EN ISO
 10545.3

Absorbs	Interior/Exterior	Frost Resistant
<input checked="" type="checkbox"/> Absorbs 0-.5%	<input type="checkbox"/> Vitreous	<input type="checkbox"/> Frost Resistant
<input type="checkbox"/> Absorbs .5-3%	<input type="checkbox"/> Semi-Vitreous	<input type="checkbox"/> Indoor Use Only
<input type="checkbox"/> Absorbs 3-7%	<input type="checkbox"/> Non-Vitreous	<input type="checkbox"/> Indoor Use Only
<input type="checkbox"/> Absorbs 7% +		

Breaking Strength

ASTM C648
 UNI EN ISO
 10545.4

PASS



Facial Dimension

ASTM c499-09
 UNI EN ISO
 10545.02

	Standard	Tolerance	Result
flatness	± 5mm	± .5%	PASS
thickness	± 6mm	± .5%	PASS
straightness	± 4.5mm	± .5%	PASS
squareness	± 5.4mm	± .6%	PASS
sides L/W	± 1.1mm / ± 4.5mm	± .5%	PASS

Chemical Resistance

ASTM C650
 UNI EN ISO
 10545.13

Allowances for:

	result
Acid	A
Bases	A
Chemicals	A

LEED V4.1 BD+C

MATERIAL AND RESOURCES

ID	Requirement/Criteria	Potential Score
MRp1	Storage and Collection of Recyclables	Required
MRC5	Construction and Demolition Waste Management	2 points ✓
MRC1	Building Life-Cycle Impact Reduction	4 points ✓
MRC2	Building Product Disclosure and Optimization - Environmental Product	1 point ✓
MRC3	Building Product Disclosure and Optimization - Sourcing of Raw Materials	2 points ✓

INDOOR ENVIRONMENTAL QUALITY

ID	Requirement/Criteria	Potential Score
IEQc2	Low-Emitting Materials	3+ points ✓

Type: **Porcelain Stoneware**

Product Line: **PALACE**

The marketing name for this product is property of CTS Pro. This same product may be marketed under different names.

PRODUCT SPECIFICATIONS - Glossy Ceramic Wall Tile

Suggested Applications

Floor Wall Residential Light Commercial Heavy Commercial Exterior Pools

*Wear can vary greatly. please consult with a professional.

Installation Suggestions

Plank Installation* Modular Setting Joint Size **1/16"**

*Install the offset the width of the plank. For professional installation, the use of leveling spacers for all plank and rectangular (ie. 12x24) format tiles is recommended.

EDGE: Straight/Pressed Rustic Rectified

FINISH: Matte Polished Structured Honed Semi-Polished Glossy

Tile Type

ceramic porcelain other through-body color-bodied glazed unglazed white-body other

Shade Variation

V1 Uniform Appearance V2 Slight Variation V3 Moderate Variation V4 Substantial Variation

THICKNESS: **9mm** **# OF FACES:** **14**

Stain Resistance

ASTM C1378-04
 UNI EN ISO
 10545.14

5

- 5: Removed after 5 minutes (hot water running)
- 4: Removed by manual cleaning (weak detergent)
- 3: Removed by mechanical cleaning (strong detergent)
- 2: Removed by immersion (24 hrs in suitable solvent)
- 1: Stain not removed

Wear Resistance

PEI RATING
 UNI EN ISO
 10545.7

- Class 1: Walls only
 - Class 2: Residential floors w/minimal abrasive traffic
 - Class 3: Residential interiors/light commercial traffic
 - Class 4: Medium commercial applications
 - Class 5: All commercial applications/heavy traffic
- *Wear can vary greatly. please consult with a professional.

Chemical Resistance

ASTM C650
 UNI EN ISO
 10545.13



Allowances for:

	result
Acid	A
Bases	A
Chemicals	A

Water Absorption

ASTM C-373
 UNI EN ISO
 10545.3



<input type="checkbox"/> Absorbs 0-.5%	<input type="checkbox"/> Absorbs .5-3%	<input type="checkbox"/> Absorbs 3-7%	<input checked="" type="checkbox"/> Absorbs 7% +
Impervious Interior/Exterior Frost Resistant	Vitreous Interior/Exterior Frost Resistant	Semi-Vitreous Indoor Use Only	Non-Vitreous Indoor Use Only

Facial Dimension

ASTM c499-09
 UNI EN ISO
 10545.02

	Standard	Tolerance	Result
flatness	±5mm	±.5%	PASS
thickness	±6mm	±.5%	PASS
straightness	±4.5mm	±.5%	PASS
squareness	±5.4mm	±.6%	PASS
sides L/W	±1.1mm ±4.5mm	±.5%	PASS

Type: **Ceramic Stoneware**

Product Line: **PALACE**

The marketing name for this product is property of CTS Pro. This same product may be marketed under different names.



CTS | Pro⁺